



# Technical Data Sheet

## AJBaspar

**WATER BASED ACRYLATE**  
ADHESIVE FOR VACUUM MEMBRANE

### AJ 300

#### Technical properties

Appearance	White liquid
Viscosity at 20 °C	4000-5000 cps
pH value at 20 °C	7-8
Solid content (%)	51
Activation temperature (°C)	60- 65
Shelf time	12 months

#### Characteristics

- Easy to apply
- Free of solvent
- Low activation temperature
- Good smooth finish surface
- Good endurance bonding strength

#### Instructions for Use

The AJ 300 can be processed in one-component without any additional hardener. This adhesive is sprayed with an appropriate spray gun (Nozzle size 1.8-2 mm). The pieces can be placed into the membrane or vacuum press drying time (depending on ambient temperature and humidity).

#### Storage

Keep the adhesive in the dry environment and temperature between 10-30 °C

#### Cleaning

Machines and equipment may be cleaned after use with warm or cold water

#### Packaging

10 kg gallon

AJ BASPAR ARMAN NOVIN CO.

Isfahan Science & Technology Town, Isfahan, Iran

[WWW.AJBASPAR.COM](http://WWW.AJBASPAR.COM)